

Adhesive tapes

Isotape 51600 PV3

- High tensile strength
- Resistance to edge tear
- Oil and Varnishes resistance
- Nynas and Shell oils resistant
- up to 155°C Temperature usage
- Chlorine free

		Value	Test norm
Backing		Woven polyester	
backing thickness	mm	0.125	ASTM-D1000
Total thickness	mm	0.180	ASTM-D1000
Width	mm	850	
Length	Mt.	50	
Color		White	
Tensile strength	N/25 mm	300	ASTM-D1000
Elongation	%	10	ASTM-D1000
Adhesive		Thermosetting acrylic	
Adhesion to steel	N/25 mm	11.8	ASTM-D1000
Breakdown voltage	kV	≥1.7	ASTM D-149
Thermal class	°C	130	

General description

51600PV3 is a woven polyester backing system that provides a high tensile strength. The aggressive adhesive makes this tape ready for a variety of heavy duty insulating and holding applications. It offers resistance to edge tear for a large number of applications. Excellent conformability remains flexible after curing. Also a thermosetting acrylic adhesive system gives the tape excellent solvent and oil resistance (resistant to Nynas Nytro 10 GBN oil for immersed transformer).

Application

- Coil outer wraps
- Final bandage for transformer coil
- Electrical motor and generator binding
- Protection and end wrapping for oil immersed coil
- also suitable for stator winding for electro motors

Storage Conditions

For the best shelf time storage temperature should be:

- 15°C to 25°C
- relative humidity: 40% +/- 30%

Shelf life

51600PV3 can be stored at room temperature for at least 12 months.

The product properties set forth in this data sheet are based on the results of testing of typical material produced by the affiliated companies of Von Roll Holding Ltd. (underneath referred as Von Roll). Some variation in product properties is typical. Comments or suggestions relating to any subject other than product properties are offered only to call the end-user's or other person's attention to considerations which may be relevant in the independent determination of the use and/or manner of use of product. Von Roll does not claim or warrant that the use of its product will have the results described in this data sheet or that the information provided is complete, accurate or useful. The user should test the product to determine its properties and its suitability for the intended use. Von Roll expressly disclaims any liability for any damage, harm, injury, cost or expense to any person resulting directly or indirectly from that person's reliance on any information contained in this data sheet. Nothing contained in this data sheet constitutes representation or warranty as to any matter whatsoever. Von Roll makes no warranties whatsoever in this data sheet, expressed or implied, including any implied warranty or fitness for a particular use or purpose. Von Roll shall in no event be liable for incidental, exemplary, punitive or consequential damages.