



- TECHNICAL DATA SHEET -

SYNTHITE EV-43/742-D
GREEN INSULATOR
180°C (Green insulating protective enamel)

DESCRIPTION

SYNTHITE EV-43/742-D Green Insulator (class H) is a protective high temperature insulating enamel that dries very quickly, forming a tough and flexible film with excellent heat and chemical resistance. It has the following outstanding properties:

- Very fast air drying.
- Excellent chemical resistance.
- Oil and moisture resistant.
- Hard, smooth, abrasion resistant film.
- Excellent adhesion.
- Thermal class: 180°C.

CHARACTERISTICS

Physical properties	
Color.	Red
Specific gravity at 25°C	1100±50g/l
Viscosity in Ford Cup n. 4 at 25°C	110-150"
Viscosity in ISO Cup n.6 at 25°C	70-110"
Build up, D.F.T. (ASTM D-115-55)	0,075 / 0,100 mm.
Thinner.	Dolph's T-200
Air-drying time (on a copper plate)	Set to touch: 60'
Corrosive effects on copper	None
Arc resistance (ASTM D-495) in a thickness >60μ	> 200"

Electrical Properties	
Dielectric Strength (dry)	2000 Volts/ 0,025 mm.
Dielectric Strength (after 24h. dipping into water)	1200 Volts/ 0,025 mm.
CTI according to IEC 60112	600 M

Chemical resistance on dry film 40 micron. Drying time 24h at 25°C + 24h at 60°C ISO 2812 Method 2 168h exposure			
Evaluation acc to ISO 4628/2-3-4	Blistering	Rusting	Cracking
Water	0	0	0
Acid (10% Sulfuric Acid)	0	0	0
Alkali (1% Sodium Hydroxide)	0	0	0
Salt Water	0	0	0

Resistance to oil transformer(IEC 60296) ASTM D 115-55	Test Passed
Corrosion resistance (salt spray) ISO 9277	200h
Humidity resistance ISO 6270	72h



APPLICATION

SYNTHITE EV-43/742-D Green Insulator dries very quickly to a uniform, glossy finish that gives a superior abrasion resistance and an excellent adhesion to most surfaces.

It is suitable as a protective coating for stator coils, transformer coils, armature coils, bus bars, field coils, control coils, commutator ends, collector rings, oil reservoir interiors, switch bases, porcelain, molded bakelite, solenoid coils, motor frames and so on.

SYNTHITE EV-43/742-D is supplied with a viscosity suitable for application by brush. For spraying application, it must be thinned with 15% about of Dolph's T-200 thinner.

STORAGE AND SHELF LIFE

Store in a cool dry place (max 30°C) away from direct sunlight. Protect from moisture and humidity.

Shelf life is 24 months when stored in closed container at max 30°C

SAFETY AND ENVIRONMENT

SYNTHITE EV-43/742-D must be intended for industrial/professional use only. Refer to the safety data sheet for any further detail.

Warning: All the information and application instructions concerning this product are based on technical specifications that we consider reliable, and are provided by way of example, according to our application experience. They do not establish any guarantee but only represent a starting point subject to alterations, according to the application and the kind of material to be treated. Before the product's use the utilizer must determine the suitability for the intended use undertaking all risks and responsibility for whatever may happen in connection with the application. The producer and/or seller will not be considered responsible for any accident, loss or damage (immediate or consequent) originating from the use and/or the inability to use the concerned product. Albesiano Sisa Vernici srl reserves the right to change or modify at any time and without any notice the technical specifications of the product described in this data sheet.

File: EV-43-742D eng	Issued on: 08.05.15	Updated on: 16.03.2016	This document cancels and replaces all previous ones.
-------------------------	------------------------	---------------------------	---